


Everacid
Blue A-RRL


特性 Properties

溶解度 Solubility	90°C	40G/L
	90°C→25°C	40G/L
顏色濃度 Color consistency	鎢絲燈 Tungsten Lamp	較紅味,較鈍 Redder,duller
	TL84 白日光燈 TL 84 Lamp	較紅味,較鈍 Redder,duller
金屬離子的影響 Effect of metal In dye bath	鐵 Iron	4
	銅 Copper	4-5
	鉻 Chrome	3
半尼龍混紡之污染性 Staining on half nylon blends	醋酸纖維 Acetate	4
	棉 Cotton	2-3
	聚酯 Polyester	4
	壓克力 Acrylic	5
拔染性 Dischargeability	氯化亞錫 Stannous chloride	1
	Decrolin	2
剝色性 Decolouration	1	


試驗項目 Test item		固色前 Before fixing			固色後 After fixing		
		N	PA	Co	N	PA	Co
水洗堅牢度 Washing	AATCC 2A	3	1-2	3	5	4-5	5
	ISO 105-C02	3	1-2	3	4-5	3	4-5
	ISO 105-C03	2	1	2-3	3-4	1-2	3-4
	ISO C06-B2S	3	1-2	3-4	4-5	3	4-5
	ISO C06-C2S	2-3	1	2-3	3	1-2	3-4
耐水堅牢度 Water	ISO-E01	4-5	1-2	3-4	5	4-5	5
耐海水堅牢度 Sea water	ISO-E02	4-5	1-2	3	5	4-5	5
耐汗堅牢度 Perspiration ISO-E04	酸 acid	4-5	1-2	3-4	4-5	5	5
	鹼 alkaline	4-5	1	2-3	4-5	3-4	4
耐氯水堅牢度 Chlorinated water ISO-E03	20 ppm	1-2			1-2		
	100ppm	1			1-2		
磨擦堅牢度 Rubbing ISO-X12	乾 Dry	5			5		
	溼 Wet	5			5		
熱壓堅牢度 Hot pressing ISO-X11	立即 Immed.	4-5					
	4 小時後 After 4hr	5					
日光堅牢度 Light	ISO-B02	0.1% o.w.f	0.5% o.w.f	1% o.w.f.	2% o.w.f.		
		6	6	6	>6		




0.1%



0.5%



1.0%




2.0%

以 MESITOL NBS 2% 固色後 (After fixed with MESITOL NBS 2%)


Everacid Blue A-RRL

(C.I. Acid-Blue 62)

昇溫上色曲線
Step dyeing



PH 依存性
Dependency on pH



- ◇ 明亮帶紅味藍色
Brilliant reddish blue
- ◇ 均染性佳
Good level dyeing
- ◇ 甚至淺色也日光堅牢度佳
Good light fastness even in pale shades
- ◇ 適合印花加工
Suitable for printing
- ◇ 遮蓋性佳
Good coverage of barre

染色特性 Dyeing properties

瞬染性 Strike	大 large
移染性 Migration	極佳 very good
橫條遮蓋性 Coverage of barre	極佳 very good
尼龍和羊毛相對染料分配性 Relative dye distribution between polyamide and wool fiber	尼龍>>羊毛 PA>>Wool
羊毛的色光與尼龍比較 Shade on wool as compared with polyamide	較綠味 greener